



## IN THE U.S. PATENT AND TRADEMARK OFFICE

Applicant: Toshihiro TAI  
For: Thermoplastic resin composition  
Serial No.: 09/869 747                      Group: 1714  
Filed: June 29, 2001              Examiner: Wyrozebski Lee  
Attorney docket  
No.: Furuya Case 1391

The Commissioner of Patents and Trademarks  
Alexandria, VA 22313-1450

## DECLARATION UNDER 37 CFR 1.132

I, Toshihiro TAI, hereby declare as follows:

I am the sole inventor of the invention described and claimed in the instant patent application.

I have carried out additional tests. Test procedures and results are described below.

A composition of Comparative Example 7 was prepared and tested in the same manner as Example 3 as shown in the instant patent application except for using components shown below in amounts shown by percent by weight.

(A) nylon 6	28
(A) ABS resin	12
(B) carbon fiber	30
(C) aluminum borate whisker	20
red phosphorous flame retardant	5
magnesium hydroxide	5

Serial No. 09/869 747 - page 2

Test results are shown below.

modulus of flexural elasticity (MPa)	24500
Izod impact strength	55
Warp (mm)	0.5
Fluidity (MI) (g/10 min)	37
Flammability 0.8mm	V0

It is noted from the test results that Comparative Example 7 is inferior to Example 3 shown in the original description of the instant application in view of Izod impact strength and fluidity. That is, that has a lower Izod impact strength and a larger fluidity than this. The results are caused by no maleic acid-modified ABS resin incorporated.

I hereby declare that all statements made herein of any own knowledge are true, and that all statements made on information and belief are believed to be true; and further, that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United State Code, and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

Dated: February 25, 2009

Toshihiro Tai  
Toshihiro TAI